

Rekord 2B-STEEL-L

machine taps



applications - materials		cutting speed vc in m/min		
		min.	recommended	max.
P1.1 Construction steels, Free-cutting steels, etc.	$\leq 600 \text{ N/mm}^2$	5	15	25
P2.1 Construction steels, Cementation steels, Steel castings, etc.	$\leq 800 \text{ N/mm}^2$	5	10	20
P3.1 Cementation steels, Heat-treatable steels, Cold work steels, etc.	$\leq 1000 \text{ N/mm}^2$	2	8	15
N2.2 Copper-zinc alloys (brass, long-chipping)	$\leq 550 \text{ N/mm}^2$	10	20	40